

BASIC

Product Data

- DECKING
- CLADDING

Scientific Name: Pinus Sylvestris
Family: Pinaceae
Origin: North Europe
Biological Durability Class: III



Intense Thermal Treatment

Density (20/65) [kg/m ³]	460
Modulus of rupture (MOR) [MPa]	35
Modulus of elasticity (MOE) [GPa]	8,9
Compressive Strength [MPa]	46
Static Hardness (Janka) [N]	1839

* Values in parentheses correspond to standard deviation

FSC® or PEFC certified in accordance with EUDR,
UKFRC, EPBC ACT, BEL and Lacey Act

Lorem ipsum



Official partner of natural fire retardant solutions



Rot-Resistant



High Dimensional
Stability



Longer-Lasting

ESSENTIAL
DURABILITY
AND QUALITY



The mark of
responsible forestry
FSC® C121009

Ask us about our Certified Products

TIMBRA
TECH Innovating Nature
Building Futures